



SUPERIOR BOND TO BLOCK, STONE & TIMBER

Titebond® PROvantage Landscape Construction Adhesive is specifically designed for use on pavers, retaining walls, stone, brick, block, wood and most common building materials used in landscaping. The professional strength formula is waterproof and works well in extreme weather conditions to provide a long lasting bond. Exceeds the requirements of ASTM D3498, APA AFG-01 and ASTM C557.

PROvantage
VOC-Compliant Solvent

Prevents Wall Shifting / Extrudes 0°F to 100°F /
Wet & Frozen Lumber and Brick & Stone / All Weather /
Durable Bond / Waterproof

LANDSCAPE

Best Choice for All Around Use

PROvantage

VOC-Compliant Solvent

Liquid Nails Landscape Block & Stone

Loctite PL 500 Landscape

	PROvantage VOC-Compliant Solvent	Liquid Nails Landscape Block & Stone	Loctite PL 500 Landscape
Type	Proprietary Synthetic Polymer	Water Based	Synthetic Rubber & Resin
VOC	< 70 g/L	< 70 g/L	7.5 g/L
Viscosity	130,000 cps	400,000 cps	210,000 cps
Color	Beige	White	Light Tan
Waterproof	Yes	Water-Resistant	Yes
Odor	Solvent	Very Mild Latex	Acetone Like
Application Temp	0°F - 100°F	22°F - 120°F	0°F - 100°F
Cold Weather Extrusion*	0°F - 145 lbf / 40°F - 80 lbf Easiest to Extrude	0°F - Adhesive Froze / 40°F - 103 lbf	0°F - 214 lbf / 40°F - 136 lbf
Extrudability at 0°F	Moderate to Light Force	Frozen, Unable to Extrude	Moderate to Heavy Force
Working Time	20 Minutes	10 Minutes	15 Minutes
Peak Strength	Wet Materials - 28 Day (340.5 PSI) Frozen Materials - 28 Day (384 PSI)	Wet Materials - Not Recommended for Wet Surfaces Frozen Materials - 28 Day (78.9 PSI)	Wet Materials - 28 Day (340.2 PSI) Frozen Materials - 28 Day (326.9 PSI)
Build-Up of Strength	1 Day: 11.1 PSI / 3 Day: 190.7 PSI 7 Day: 288.7 PSI / Full Cure: 478.7 PSI Builds Strength Faster	1 Day: 1.0 PSI / 3 Day: 11.3 PSI 7 Day: 33.0 PSI / Full Cure: 385.6 PSI	1 Day: 10.7 PSI / 3 Day: 42.5 PSI 7 Day: 215.4 PSI / Full Cure: 322.4 PSI

Titebond
THE PRO'S ADVANTAGE

* This shows the amount of force it took to extrude each adhesive (in inch-pound units) at the given temperatures. A calibrated pull test machine was used.

Visit Titebond.com for the most up-to-date product information.

Franklin International

Columbus, Ohio 43207 614.443.0241

Technical Service 1.800.347.4583

© 2019 01455_4129bcm FF1211

